

TIMBER SPECIES

American White Ash – *Fraxinus americana*

Wood Appearance

Colour – The heartwood ranges in colour from a creamy white to a light brown with a wide light band of sapwood.

Grain – Straight and slightly open coarse grain

Wood Properties

Density – 600 kg/m³

Durability – Class 2 – Highly resistant to decay when fully exposed to the weather, clear of the ground and well drained with free air circulation. Only moderately decay resistant in the ground.

Hardness – Not Available

Identification Features

Sapwood – Is a distinctly lighter colour to the heartwood

Heartwood – Ranges in colour from a creamy white to a light brown

Texture – Due to the difference in the spring and late wood, the grain gives the timber a pronounced flame pattern when crown cut.

Wood Structure

Growth Rings – Not Available

Vessels – Not Available

Parenchyma – Not Available

Rays – Not Available

Other Features

Burning Splinter Test – Not Available

MASTER WOODTURNING
37 LANCASTER STREET
INGLEBURN NSW 2565

P: 02 9829 5000
F: 02 9829 5100
E: Sales@masterwoodturning.com.au

We do anything when it comes to wood