

# TIMBER SPECIES

## **Anegre** – *Aningeria Altissima*

### Wood Appearance

**Colour** – Heartwood is cream to tan with pinkish tinge. Generally even in colour.

**Grain** – Generally with a straight grain but sometimes it can be wavy

### Wood Properties

**Density** – 540 kg/m<sup>3</sup>

**Durability** – Not Available

**Hardness** – Not Available

### Identification Features

**Sapwood** – Not distinguishable from the heartwood

**Heartwood** – Cream to tan with pinkish tinge

**Texture** – Not Available

### Wood Structure

**Growth Rings** – Not Available

**Vessels** – Not Available

**Parenchyma** – Not Available

**Rays** – Not Available

### Other Features

**Burning Splinter Test** – Not Available

**MASTER WOODTURNING**  
37 LANCASTER STREET  
INGLEBURN NSW 2565

**P: 02 9829 5000**  
**F: 02 9829 5100**  
E: [Sales@masterwoodturning.com.au](mailto:Sales@masterwoodturning.com.au)

*We do anything when it comes to wood*