

# Surian – *Toona surianii*

## Wood Appearance

**Colour** – The heartwood is a reddish brown.

**Grain** – Grain can be either straight or interlocked.

## Wood Properties

**Density** – 400 kg/m<sup>3</sup>

**Durability** – Class 2 – Highly resistant to decay when fully exposed to the weather, clear of the ground and well drained with free air circulation. Moderately decay resistant in the ground.

**Hardness** – Not Available

## Identification Features

**Sapwood** – Not available

**Heartwood** – The heartwood is a reddish brown.

**Texture** – Texture is moderately coarse

## Wood Structure

**Growth Rings** – Not Available

**Vessels** – Not Available

**Resin Canals** – Not Available

**Parenchyma** – Not Available

**Rays** – Not Available

## Other Properties

**Odour** - This timber has a characteristic cedar like fragrance due to the exudation of an essential oil, which is sometimes present on the timber's surface.

**MASTER WOODTURNING**  
37 LANCASTER STREET  
INGLEBURN NSW 2565

**P: 02 9829 5000**  
**F: 02 9829 5100**  
E: [Sales@masterwoodturning.com.au](mailto:Sales@masterwoodturning.com.au)

*We do anything when it comes to wood*