

Victorian Ash (Mountain Ash) – *Eucalyptus regnans*

Wood Appearance

Colour – The heartwood is usually pale pink or straw. The Sapwood is not distinguishable from the heartwood.

Grain – Usually straight but sometimes wavy

Wood Properties

Density – N/A kg/m³

Durability – Class 3 – Moderately resistant to decay when fully exposed to the weather, clear of the ground and well drained with free air circulation. Not recommended for in-ground use, or in external decking applications.

Hardness – Not Available

Identification Features

Sapwood – Not clearly distinguishable

Heartwood – Pale pink or pale straw

Texture – Moderately coarse

Wood Structure

Vessels – Not Available

Parenchyma – Not Available

Rays – Not Available

Other Features

Burning Splinter Test – Not Available

Growth Rings – Conspicuous

MASTER WOODTURNING
37 LANCASTER STREET
INGLEBURN NSW 2565

P: 02 9829 5000
F: 02 9829 5100
E: Sales@masterwoodturning.com.au

We do anything when it comes to wood